

KÖSTER KSK Primer BL

Technical guideline / Article number **7.32**
Issued: January 14, 2010

Solvent free, strongly adhesive primer for KSK-membranes on polymer-modified bitumen basis

Features

KÖSTER KSK Primer BL is a solvent free, strongly adhesive, thin fluid primer for KSK-membranes on the basis of bitumen with a high polymer content. It is characterized by very good adhesion to dry and moist mineral substrates.

Technical data

Solid particle content	> 55 %
Minimum application temperature	+ 5 °C
Curing time (at 20 °C)	24 hours
Application of next layer (at 20 °C)	approx. 3 – 4 hours
(at 10 °C)	approx. 5 – 7 hours

Packaging

15 l canister

Storage

Store the material cool but frost free; in originally sealed packages, it can be stored for 12 months.

Technical guidelines cited

KÖSTER KSK membranes

Art. No. 10.311 – 10.361

Field of application

KÖSTER KSK Primer BL is a primer for preparing substrates for the application of KÖSTER KSK membranes.

Application

KÖSTER KSK Primer BL is applied thoroughly undiluted in one coat using a roller, or brush or a suited spraying device.

Consumption

250 - 400 g / m² per coat (in case of strongly absorbent substrates, two coats are necessary – total consumption approx. 500 g / m²)

Cleaning of tools

Clean tools immediately after use with clean water.

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.